



MORTARS

QUICK-SETTING MORTAR

TECHNICAL DEFINITION

Ready-to-mix mortar for interior and exterior use on floors and walls.

Fields of application: quick sealing, blocking, fixing, minor repair work.

ACCEPTED SUBSTRATES

Concrete, stone, brick.

PRECAUTIONS FOR USE

The temperature during application and drying must be between 5 and 30°C. Do not use under freezing weather, rain or full sun. Do not use on wet surfaces. Do not apply onto plaster.

Due to the quick setting time, always proceed with small quantities at a time.

Product labelled as hazardous. Contains cement: gloves should be worn. Refer to the safety label on the packaging. Observe the precautions for use and the safety advice. Safety data sheet available at www.quickfds.com, read before use.

PREPARATION OF SURFACES

The surfaces must be clean, free of dust, hard and free of any trace of separation agent.

High porosity surfaces or surfaces treated under high heat must be dampened beforehand.


MIXING FACTOR

1 litre of water for 5 kg of quick-setting mortar.

PACKING. 5 kg bags.

STORAGE

6 months in unopened original packing protected from damp.



ADVANTAGES

- Quick drying.
- Can be used indoors and outdoors.

GREY FINE-GRAIN MORTAR

TECHNICAL DEFINITION

Ready-to-mix mortar for restoration and finishing work on interior and exterior walls.

ACCEPTED SUBSTRATES

Concrete, mortar, stone, brick, filler.

PRECAUTIONS FOR USE.

The temperature during application and drying must be between 5 and 30°C. Do not use under freezing weather, rain or full sun. Do not use on wet surfaces. Do not apply onto plaster.

Due to the quick setting time, always proceed with small quantities at a time.

Product labelled as hazardous. Contains cement: gloves should be worn. Refer to the safety label on the packaging. Observe the precautions for use and the safety advice. Safety data sheet available at www.quickfds.com, read before use.

PREPARATION OF SURFACES

The surfaces must be clean, free of dust, hard and free of any trace of separation agent.

High porosity surfaces or surfaces treated under high heat must be dampened beforehand.

MIXING FACTOR

1 litre of water for 5 kg of fine-grain mortar.

PACKING 5 kg bags.

STORAGE

6 months in unopened original packing protected from damp.



ADVANTAGES

- Can be used indoors and outdoors.
- Superb finish.
- No cracking.

